

0980

MIXING INSTRUCTIONS

0980 Soilmoisture Epoxy Kit

March 2005

INSTRUCTIONS

Your epoxy kit contains 2 bottles per kit: 1 each hardener, 1 each epoxy. For mixing by volume, take equal parts by volume of hardener and epoxy. For mixing by weight, use a scale, weigh epoxy, then take 10 parts epoxy and 8 parts hardener.

Stir thoroughly.

MIXING PROPORTIONS

By volume: 1:1

By weight: 10 parts epoxy : 8 parts hardener

WORK LIFE

50-70 minutes @ 77° F

FULL CURE


at 77° F: 8 hours

SHELF LIFE

12 months

CAUTIONS

For your convenience, we are attaching the current Material Safety Data Sheets or MSDS for these materials. Read both MSDS sheets for both the resin and hardener.



© Copyright 1999
All rights reserved

0898-0980

SOILMOISTURE EQUIPMENT CORP.

P.O. Box 30025, Santa Barbara, California 93105 USA

Telephone: (805) 964-3525 • Fax: (805) 683-2189

Website: <http://www.soilmoisture.com> • email: sales@soilmoisture.com

